

## Claims

1. An ink jet recording paper characterized by using mercerized pulp as a fiber material.
2. The ink jet recording paper according to claim 1 characterized in that the ratio of the mercerized pulp used is from 10 to 100% by weight of the entire fiber material.
3. The ink jet recording paper according to claim 1 ~~or 2~~ characterized in that a liquid transfer length in the Bristow's method according to J. Tappi No. 51 - 87 is 100 mm or less, when distilled water has been set at 50  $\mu$ L in a head box of 1 mm slit width and 15 mm slit length and the moving speed of a test specimen has been set to 5.0 mm/sec.

Add  
A1

Add B1

Add C1

Add D1